Aboutus

The success of a brand lies in its ability to evolve and stand ahead of its time with a pioneering vision. Our and its exceptional offering is a result of vision, demand, and objective of delivering products that add iconic values to the spaces of customers. It is also a passionate endeavor encouraged and inspired by the efforts of sustainability for a better tomorrow.

Surfaces that resonate with excellence

IMAGINE YOUR SPACE WITH SEAMLESS POSSIBILITIES

Think Big and Different with the our. The our Surface of this Collection adds a Distinctive Character to a Place with its Grand Size of 800x2400mm, the Durable Thickness of 15mm. and many Enchanting Designs.

BIG SIZE SLABS

80x240cm

15mm Thickness

The 15mm thickness of the surfaces assures that spaces are sturdy, durable, and resilient with their toughness. These surfaces allow you to enjoy your spaces without worry.




The Our Surface transforms the perspective of design with its attractive style.


The ever-elegant appeal of the matt finish and the jaw-dropping designs of the our Surfaces can fabricate any space ever imagined. Their modish style and suave aura are perfect to embellish different parts of a room to give it a contemporary feel. These tiles are ideal for applications on staircases, countertops, furniture, fireplace, and much more.

SURFACES THAT BRINGE DESIGN VISION TO LIFE



FABRICATE Comfortable Lifestyle






The Our Surfaces encompass the spirit of sophistication and effortless elegance in their graceful semblance. The tiles of this collection dress-up places with eternal charm and style.

EDGE PROFILES





Ogee

JOINT POSSIBILITIES



1.1.4 THE MARKET A PROPERTY AND Lines 1 p.















Waterproof Surface












T<mark>ype</mark> Full Body



Flexural Strength

Frost Resistance














KOTA

Finish Glossy / Matt

T<mark>ype</mark> Full Body



T<mark>ype</mark> Full Body











Waterproof Surface











STEEL GREY

Finish Glossy / Matt

Type Full Body

CRYSTAL BLACK

Finish Glossy / Matt







FOSSIL GREY


Finish Glossy / Matt



CHOCO

Finish Glossy / Matt


Type Full Body




MANUALLY TRANSPORTING IMMODERATE


Only for 1/4" Slabs

MOVING A IMMODERATE TILE






RAISING A IMMODERATE TILE ONTO A BENCH




X INCORRECT


HANDLING IMMODERATE TILE FOR WALL



X INCORRECT



✓ CORRECT



✓ CORRECT

WORKING WITH THE VARIOUS VERSIONS OF **IMMODERATE**

CUTTING WITH DIAMOND DISCS



Our products can be cut using diamond discs fitted onto the hand-held electrical grinding machine. The speed of Disc rotation must be high (>10000 RPM) and should have a low feed rate (< 1 m/min). Itmay be required to cool the disc with water. Recommended discs are the thin typesgenerally used for cutting porcelain stoneware. The surface should be kept on a FLAT base while cutting without any gap underneath

DRILLING



You can use cutting discs fitted to battery-operated screwdrivers or angle grinders, electrical drills as an alternative.


INTERNAL CUT / L-SHAPED CUT


When using these tools: -Cool the point being drilled with water working on

EDGE-FINISHING









To get internal and L-shaped corners & to reduce the risk of breakage. round o the vertex of the internal corner using bits with a radius of at least 5mm. Then cut with diamond discs, be cautious to stop moving the cutting tool forward. To drill and cut using diamond discs, follow the instructions provided above.

-Don't put too much pressure and bear in mind the resistance of the type of laminated stoneware you are

-If you are using tungsten bits, start drilling at a low speed -If you are using drills or screwdrivers, do not select hammering mode

SUPPORT

Technical Specifications

CHARACTERISTICS	STANDARD AS PER ISO-13006/En14411 GROUP	VALUES	TEST METHOD
	REGULATORY PI	ROPERTIES	
Deviation in Length & Width	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Deviation in Thickness	<u>+</u> 5%	<u>+</u> 5%	ISO 10545-2
traightness of Sides	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545 - 2
lectangularity	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545 - 2
Surface Flatness	<u>+</u> 0.5%	<u>+</u> 0.3%	ISO 10545 - 2
Color Difference	∆E<1.00	∆E<0.30	ISO 10545 - 16
Blossiness	As per Mfg.	>90%	Gloss Meter 60
	STRUCTURAL PI	ROPERTIES	
Vater Absorption	≤0.5 %	<u>≤</u> 0.06 %	ISO 10545-3
Apparent Density	As Per Mfg.	>2.20 g/cc	ISO 10545-3
	MASSIVE MECHANIC	AL PROPERTIES	
Modulus of Repture	Min 35N/mm ²	Min.40N/mm ²	ISO 10545 - 4
Breaking Strength	Min. 1300 N	Min. 7200 N	ISO 10545 - 4
mpact Resistance	As per Mfg.	Min. 0.55	ISO 10545 - 4
	SURFACE MECHANIC	AL PROPERTIES	
Surface Abrasion Resistance	As per Mfg.	Min. class 3	ISO 10545-7
Noh's Hardness	As per Mfg.	Min. class 4	BS EN 15771
	THERMO HYGROMET	RIC PROPERTIES	
Frost Resistance	As Per Mfg.	Frost Proof	ISO 10545-12
Thermal Shock Resistance	Min. 10 Cycle	Min. 10 Cycle	ISO 10545-9
Noisture Expansion	Max. 0.6mm/m	Max. 0.02mm/m	ISO 10545 - 10
hermal Expansion	Max. 9.0 x 10 ⁻⁶	Max. 6.0x10 ⁻⁶	ISO 10545-8
	CHEMICAL PRO	OPERTIES	
Chemical Resistance	As Per Mfg.	No Damage	ISO 10545-13
Stain Resistance	Resistant	Resistant	ISO 10545-14

CHARACTERISTICS	STANDARD AS PER ISO-13006/En14411 GROUP	VALUES	TEST METHOD
I	REGULATORY PR	OPERTIES	
Deviation in Length & Width	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Deviation in Thickness	<u>+</u> 5%	<u>+</u> 5%	ISO 10545-2
Straightness of Sides	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Rectangularity	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Surface Flatness	<u>+</u> 0.5%	<u>+</u> 0.3%	ISO 10545-2
Color Difference	∆E<1.00	∆E<0.30	ISO 10545-16
Glossiness	As per Mfg.	>90%	Gloss Meter 60
	STRUCTURAL PF	20PERTIES	
Water Absorption	<u>≤</u> 0.5 %	<u>≤</u> 0.06 %	ISO 10545-3
Apparent Density	As Per Mfg.	>2.20 g/cc	ISO 10545 - 3
·	MASSIVE MECHANIC	AL PROPERTIES	
Modulus of Repture	Min 35N/mm ²	Min.40N/mm ²	ISO 10545 - 4
Breaking Strength	Min. 1300 N	Min. 7200 N	ISO 10545 - 4
mpact Resistance	As per Mfg.	Min. 0.55	ISO 10545 - 4
	SURFACE MECHANIC	AL PROPERTIES	
Surface Abrasion Resistance	As per Mfg.	Min. class 3	ISO 10545 - 7
Moh's Hardness	As per Mfg.	Min. class 4	BS EN 15771
	THERMO HYGROMET	RIC PROPERTIES	
Frost Resistance	As Per Mfg.	Frost Proof	ISO 10545-12
Thermal Shock Resistance	Min. 10 Cycle	Min. 10 Cycle	ISO 10545-9
Moisture Expansion	Max. 0.6mm/m	Max. 0.02mm/m	ISO 10545-10
Thermal Expansion	Max. 9.0 x 10 -6	Max. 6.0x10 -6	ISO 10545-8
·	CHEMICAL PRO	PPERTIES	
Chemical Resistance	As Per Mfg.	No Damage	ISO 10545-13

CHARACTERISTICS	STANDARD AS PER ISO-13006/En14411 GROUP	VALUES	TEST METHOD
	REGULATORY P	ROPERTIES	
Deviation in Length & Width	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Deviation in Thickness	<u>+</u> 5%	<u>+</u> 5%	ISO 10545-2
Straightness of Sides	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Rectangularity	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Surface Flatness	<u>+</u> 0.5%	<u>+</u> 0.3%	ISO 10545-2
Color Difference	∆E<1.00	∆E<0.30	ISO 10545-16
Glossiness	As per Mfg.	>90%	Gloss Meter 60
	STRUCTURAL P	ROPERTIES	
Water Absorption	<u>≤</u> 0.5 %	<u><</u> 0.06 %	ISO 10545-3
Apparent Density	As Per Mfg.	>2.20 g/cc	ISO 10545 - 3
·	MASSIVE MECHANIC	AL PROPERTIES	
Modulus of Repture	Min 35N/mm ²	Min.40N/mm ²	ISO 10545-4
Breaking Strength	Min. 1300 N	Min. 7200 N	ISO 10545 - 4
Impact Resistance	As per Mfg.	Min. 0.55	ISO 10545 - 4
	SURFACE MECHANIC	AL PROPERTIES	
Surface Abrasion Resistance	As per Mfg.	Min. class 3	ISO 10545-7
Moh's Hardness	As per Mfg.	Min. class 4	BS EN 15771
	THERMO HYGROMETI	RIC PROPERTIES	
Frost Resistance	As Per Mfg.	Frost Proof	ISO 10545-12
Thermal Shock Resistance	Min. 10 Cycle	Min. 10 Cycle	ISO 10545-9
Moisture Expansion	Max. 0.6mm/m	Max. 0.02mm/m	ISO 10545-10
Thermal Expansion	Max. 9.0 x 10 ⁻⁶	Max. 6.0x10 -6	ISO 10545 - 8
	CHEMICAL PRO	OPERTIES	
Chemical Resistance	As Per Mfg.	No Damage	ISO 10545-13
			1

CHARACTERISTICS	STANDARD AS PER ISO-13006/En14411 GROUP	VALUES	TEST METHOD
	REGULATORY PI	ROPERTIES	
Deviation in Length & Width	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545-2
Deviation in Thickness	<u>+</u> 5%	<u>+</u> 5%	ISO 10545-2
traightness of Sides	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545 - 2
lectangularity	<u>+</u> 0.5%	<u>+</u> 0.2%	ISO 10545 - 2
Surface Flatness	<u>+</u> 0.5%	<u>+</u> 0.3%	ISO 10545 - 2
Color Difference	∆E<1.00	∆E<0.30	ISO 10545 - 16
Blossiness	As per Mfg.	>90%	Gloss Meter 60
	STRUCTURAL PI	ROPERTIES	
Vater Absorption	≤0.5 %	<u>≤</u> 0.06 %	ISO 10545-3
Apparent Density	As Per Mfg.	>2.20 g/cc	ISO 10545-3
	MASSIVE MECHANIC	AL PROPERTIES	
Modulus of Repture	Min 35N/mm ²	Min.40N/mm ²	ISO 10545 - 4
Breaking Strength	Min. 1300 N	Min. 7200 N	ISO 10545 - 4
mpact Resistance	As per Mfg.	Min. 0.55	ISO 10545 - 4
	SURFACE MECHANIC	AL PROPERTIES	
Surface Abrasion Resistance	As per Mfg.	Min. class 3	ISO 10545-7
Noh's Hardness	As per Mfg.	Min. class 4	BS EN 15771
	THERMO HYGROMET	RIC PROPERTIES	
Frost Resistance	As Per Mfg.	Frost Proof	ISO 10545-12
Thermal Shock Resistance	Min. 10 Cycle	Min. 10 Cycle	ISO 10545-9
Noisture Expansion	Max. 0.6mm/m	Max. 0.02mm/m	ISO 10545 - 10
hermal Expansion	Max. 9.0 x 10 ⁻⁶	Max. 6.0x10 ⁻⁶	ISO 10545-8
	CHEMICAL PRO	OPERTIES	
Chemical Resistance	As Per Mfg.	No Damage	ISO 10545-13
Stain Resistance	Resistant	Resistant	ISO 10545-14

Chemical Resistance	As Per Mfg.	No Da
Stain Resistance	Resistant	Resi

SAFETY PROPERTIES

Slip Resistance	As per Mfg.	N. A.	DIN 51130
Fire Resistance	As per Mfg.	Fire Proof	N. A.

Edge Profiles

Micro bevel	Double straight rounded ed
Rounded straight edge	Half bullnose
Full bullnose	Demi bullnose
Double dupont	Dupont
Straight squared edge	L Double straight squared ed
Round edge at 45	Squared edge at 45
<u> </u>	
Cove dupont edge	Cove
$\square \checkmark$	
Step dupont edge	Ogee

CLEANING & MAINTENCE

Our products are non porous (due to their high quality raw materials, stringent production parameters and state of the art technology), hence any dust or deposited waste cannot penetrate the surface.

For most cases only a damp cloth is sufficient for cleaning.

Regular cleaning highlights the aesthetic features of the surface and gives it exceptional shine.

For highly aggressive cleaning caused by some common food and substances follow the table below.

TYPE OF STAIN	CHEMICAL PRODUCT	EXAMPLE
Grease	Alkaline - Solvent	Detergent
Oil	Solvent	Ammonia, Backing Soda
Ink	Oxidant - Solvent	Alcohol, Liquid Bleach, Nail Paint Remover
Rust	Acid	Hydrochloric Acid, Vinegar, Red Harpic
Lime	Acid	Descaling Reagent, Hydro Chloric Acid
Cement	Acid	Hydro Chloric Acid
Wine	Alkaline	Ammonia, Liquid Bleach
Coffee	Alkaline - Solvent	Ammonia, Liquid Bleach
Rubber	Solvent	Alcohol, Thinner
Plaster	Acid	Hydro Chloric Acid
Candle Wax	Solvent	Alcohol, Thinner
lodine	Oxidant	Liquid Bleach
Blood	Oxidant	Liquid Bleach
lce Cream	Alkaline	Liquid Bleach
	1	1

Note: It is recommended that any kind of stain needs to get clean immediately / as soon as possible.